KM120 (Low Temperature Sintering)






Product	D50	T.D	BET	Sintering
Name	(μm)	(g/ml)	(m²/g)	Temp.(°C)
KM120	0.15 ~ 0.30	3.0~4.5 (Reference Data)	1.5~2.5 (Reference Data)	120


The KM120 achieved low temperature sintering at 120 °C due to its optimized particle size and shape. In addition, it realizes the required properties in various applications as the conductive paste, thermal interface material, adhesive filler and etc.

Point.1 High Performance at Low Temp.



✓ Realize the Better Sintering and Better Conductivity at Low Temperature Process.

☞ Point.2 Combination with Silver Flakes



✓ For Use as an Additive to Improve the Specific Properties.

☞Point.3 Other Benefit

✓ Pre-dispersed with High Concentration in a Solvent Specified by the Customer



TOKUSEN KOGYO CO., LTD.

1081, MINAMIYAMA SUMIYOSHI-CHO ONO CITY HYOGO PREF., 675-1361 JAPAN

> TEL: +81-794-63-9003 FAX: +81-794-63-3865